

Local Phone: 203-575-9220

PRODUCT DATA SHEET

Business Hours: 8 am – 5 pm

Toll Free: 1-800-537-7663

2001 INC.  
P.O. BOX 2557 WATERBURY, CT 06723-2557  
325 THOMASTON AVE.  
WATERBURY, CT 06702

Emergency Telephone  
1-800-255-3924

PDS Date 01/25/05

Supercedes All Previous Publications

Page 1 of 1

PRODUCT NAME AND SYNONYMS: THERMOPLASTIC ONE-PART POURABLE SEALER

Typical Properties and Characteristics:

<u>Property</u>		<u>Typical Value</u>
Specific Gravity		1.37 (11.5 lbs/gallon)-1.44 (12.0 lbs/gallon) (1.38 kg/liter) (1.44 kg/liter)
Viscosity (Brookfield RTV), cps		Shelf leveling 20,000-50,000
Color		White
Odor		Mild ester smell (mint) when wet. Odorless when dry.
Elongation @ Break, % - (7 day ambient cure)	ASTM D-0412	450
Hardness, (Shore A)	ASTM C-0661	25-35
Tack Free Time -@ 70 degrees F. (21 degrees C)	ASTM C-0679	Less than 1 hour
Low temperature flex	PASS	Minus 20 degrees F. (Minus 29 degrees C)
Shrinkage (14 day cure)		No measurable shrinkage
Service temperature	ASTM 2453	Minus 40 degrees F to 200 degrees F. (Minus 40 degrees C to 93 degrees C)
Long term weatherability -98 cycles @ 12 hours/cycle -Condensate exposure: 4 hrs @ 122°F (50°C) -U.V. exposure-8 hrs @ 158°F (70°C)	ASTM G53	No crazing or cracking
Packaging		4-0.5 gallon pouches per bucket (4-2 liter)
Weight Per Carton		29 lbs./bucket (13.15kg)
Shelf Life (unopened container)		18 months

DISCLAIMER: The information contained herein is, to the best of our knowledge and belief, accurate. However, since the conditions of handling and use are beyond our control, we make no guarantee of results, and assume no liability for damages incurred by use of this material. It is the responsibility of the user to comply with all applicable federal, state and local laws and regulations.

Prepared By: 2001 Inc.